

1. PRODUCT NAME

**Dynaflex®
Neutral Base**

2. MANUFACTURER

Neyra Industries, Inc.
10700 Evendale Drive
Cincinnati, Ohio 45241

Phone: 513-733-1000
Toll Free: 800-543-7077
Fax: 513-733-3989
Email: info@neyra.com
Website: www.neyra.com

- **Long Lasting:** Premium acrylic polymer fortified with polyolefin fiber provides up to 50% greater wear, tensile strength and flexibility than typical clay filled acrylic coatings.
- **Convenience:** The Dynasperse pigment can be mixed at the job - only mix and use what is needed. No excess product wasted.
- **No Fading:** Dynasperse provides pure inorganic pigments, which assure rich, true color for years of service.
- **Two Year Buyer Protection Warranty:** Available from Dynaflex Licensed Applicators and Neyra Industries, Inc.

3. PRODUCT DESCRIPTION

Dynaflex Neutral Base is a premium quality, non-pigmented, acrylic emulsion. Dynaflex contains high tensile strength geotextile fibers for greater toughness, flexibility and longer service life. The product is also formulated with a surfactant package which promotes superior adhesion to concrete or asphalt surfaces. Dynaflex contains no asbestos or mercury.

Packaging:

Packaged in 5 gal. pails and 55 gal. steel drums. 260 gal. totes are available as a special order.

Color:

Dynaflex Neutral Base is a non-pigmented neutral color to which Dynasperse (Product Data Sheet 205) is added.

Basic Uses:

When mixed with Dynasperse, Dynaflex Neutral Base provides long wearing, non-fading color and texture to asphalt and concrete pavements including parking lots, tennis courts, basketball courts, playgrounds and walkways. For courts, mix designs can be adjusted to optimize speed of play and bounce requirements.

Composition:

Dynaflex Neutral Base is a blend of binders, pigments, geotextile fibers, surfactants and reological agents in a water based emulsion. Premium quality 100% acrylic polymers give

Dynaflex Neutral Base its tough, long wearing character.

The geotextile fibers offer tensile strength and dimensional stability to the product. These non-toxic inert polyolefin fibers are non-wicking and impervious to bacterial attack.

The surfactants blended into Dynaflex Neutral Base create a superior bond between the product and the pavement surface.

The reological agents allow the emulsion to maintain long shelf life and an excellent non-settling character.

Limitations:

In the liquid state, Dynaflex Neutral Base must be protected from freezing and rain. Do not store in direct sunlight or where temperature exceeds 120°F.

4. INSTALLATION

Preparatory Work:

The surface must be structurally sound, surface cured and free from all loose or foreign matter prior to the application of Dynaflex.

An asphalt recreational surface should be checked for irregularities or depressions deeper than 1/8" (birdbaths). Fill to level of surrounding surface with hot mix asphalt or Dynabinder (Product Data Sheet 261) prior to the application of Dynaflex.

On a concrete recreational surface, the finish should be wood float or light broom, not steel troweled. The surface

should be checked for depressions deeper than 1/8". Fill to level of surrounding surface with Dynabinder Quick Patch Binder prior to the application of Dynaflex.

In addition, new concrete surfaces should be lightly abraded or lightly acid-etched and then primed with Dynabinder (Product Data Sheet 261) prior to the application of Dynaflex. **Note:** *In all cases a vapor barrier beneath concrete surface is strongly recommended.*

Methods:

Dynaflex can be applied by squeegee, brush or spray. On new tennis or basketball courts, squeegee application is the recommended method.

Mix Design:

Dynaflex Neutral Base is a highly concentrated material intended to be mixed with water, Dynasperse and mineral aggregate to form a ready to use color coating.

Per 55 gallons of Dynaflex Neutral Base

Product	Amount	Yield
Water	22-28 gal.	90-100 gallons
Dynasperse	4 gal.	
Sand	300-400 lbs.	

All sand used should be clean, dry, pure silica sand, free of contaminants. Fine sand with an A.F.S. rating of 70 to 100 gives best results.

Application:

Recreational surfaces often require Dynaflex Acrylic Resurfacer (Product Data Sheet 203) prior to color coating.

There is also the option of building up an acrylic cushion underlayment with Dynaflex Cushion Base (Product Data Sheet 210) and Dynaflex Cushion Top (Product Data Sheet 211) prior to color coating.

After the resurfacer or cushion underlayment has been given adequate time to dry thoroughly, Dynaflex texture color coats shall be applied by rubber-bladed squeegee in a minimum of two applications (a third color coat is optional). As a result, on a smooth sand or rubber textured surface, consumption of Dynaflex is calculated at a rate of .05 - .1 gal./ sq. yd. /coat or 1 gal./10 to 20 sq. yds./coat.

Coverage rates can vary with the application method and the age, texture, and porosity of the pavement to be coated.

On recreational surfaces, the speed of play desired can be increased by one additional coat of Dynaflex diluted with water at the same rate as the Mix Design chart, but without the addition of silica sand.

Application must be made when ambient temperatures and pavement temperatures are above 50°F. Good drying conditions above 50°F are required during the subsequent 8 hours and no temperatures below 50°F should be anticipated for 48 hours. Night time application is not recommended. It is recommended that the area over which the application is made be opened to use only after trial shows it to be dried and sufficiently cured.

Precautions:

Wet Dynaflex Neutral Base must be protected at all times from freezing.

Keep out of reach of children. Container should be closed when not in use. Avoid breathing vapor or contact with skin or eyes. Consult specific Neyra material safety data sheet before use.

New asphalt should be allowed to cure for a minimum of 15 days prior to application and must not exhibit ribbing, crawling, nor show oil rings

when 1 gal. of clean water is poured onto the surface.

New concrete pavement should be allowed to cure for a minimum of 30 days prior to application.

5. MAINTENANCE

Proper care of the finished surface will maintain the attractive appearance and prolong the service of the Dynaflex coating system. Keeping leaves and other foreign matter off the surface and occasional flushing with clean cold water will achieve good results.

6. TECHNICAL DATA

Applicable Standards:

Dynaflex Neutral Base meets the composition and performance standards of ASTM D2833, "Architectural Paints and Coatings," when tested according to the following ASTM methods:

Drying Time:

When tested according to ASTM D1640, "set to touch" in 1 hour, dry to touch in 4 hours.

Adhesion:

When tested according to ASTM D3359A, the dried film exhibits no loss of adhesion from the substrate.

Flexibility:

When tested according to ASTM D522 B, the dried film exhibits no loss of adhesion.

Resistance to Water:

When tested according to ASTM D870, the dried film exhibits no blistering, re-emulsification or color change.

Flaking:

When tested according to ASTM D662, the dried film exhibits no flaking.

Cracking:

When tested according to ASTM D661, the dried film exhibits no cracking or breaking.

Chalking:

When tested according to ASTM D4214, the dried film exhibits no chalking or friable powder development.

Fading:

When tested according to ASTM D4587, the dried film (with Dynasperse) exhibits no fading or color loss.

Environmental Considerations:

Dynaflex Neutral Base is non-hazardous when tested according to the EPA's TCLP (Toxicity Characteristic Leaching Procedure). Dynaflex is a water based material containing less than 101 g/L (1.22 lbs./gal.) VOC content.

7. TECHNICAL SERVICES

C.S.I. formatted application specifications, material safety data sheets, special project submittals, product and application recommendations as well as assistance with special situations and field service are available.

8. WARRANTY

The above specifications on product usage are believed to be true and accurate. Neyra Industries, Inc. guarantees that all materials manufactured comply with quality standards as described in the product data sheets. Because the application, handling, weather, workmanship and equipment are beyond the control of this manufacturer, only the quality of the products as shipped is guaranteed. In no case will the liability of Neyra Industries, Inc. exceed the purchase price of the shipped materials.

9. ADDITIONAL INFORMATION

Neyra Industries, Inc. manufactures a full line of recreational surface and asphalt pavement maintenance products as well as application equipment sold and distributed nationally at our plants and through distributors and contractors. To find the supplier most convenient to you, please contact us.

NEYRA

Neyra Industries, Inc.
10700 Evendale Drive
Cincinnati, Ohio 45241

Phone: 513-733-1000

Toll Free: 800-543-7077

Fax: 513-733-3989

Email: info@neyra.com

Website: www.neyra.com